


MR[®] 221 GF Magnetic Powder Suspension



Product characteristics

- Ready to use solution for magnetic particle inspection
- Crack indication black
- Settling volume (30 min) 0.6 - 0.8 ml/ 100ml
- Average particle size da 1 - 3 µm
- (EC) No. 1272/2008 - ECO-Line
- Odour mild

Minimum shelf life / Temperatures

Aerosol / Bulk:
2 years at storage temperature
Storage: + 5 °C - + 45 °C
Application: + 5 °C - + 50 °C



Approvals / Specification

- EN ISO 9934-2
- ASME B & PV Code, Sec V
- ASME Code V, Art. 7
- RCC-M



Further information

Process description according to EN ISO 9934-1 on request or on www.mr-chemie.de/en. For further information see Material Safety Data Sheet and certificate 3.1. For additional equipment please visit our Homepage or contact our sales team.

Suggested products

Pre-cleaner: MR[®] 71, MR[®] 79, MR[®] 85, MR[®] 88, MR[®] 3001, MR[®] 3002
Contrast paint: MR[®] 72, MR[®] 725, MR[®] 726
Test block: Reference-Testblock 1, Reference-Testblock 2 & ASTM Testblock
Measuring device: Field Strength Meter, UVA/Lux, Luxmeter
Hand magnet: MR[®] 50, MR[®] 56

Delivery form



Technical changes reserved!